



# Technical Data Sheet

## Quality Specification

### Testliner 3

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m <sup>2</sup> ]	[kPa]	[kPa m <sup>2</sup> /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 % ≤ 200 g/m <sup>2</sup> ± 4 % > 200 g/m <sup>2</sup>	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	80	160	2,0	1,50	1,40
	90	180	2,0	1,60	1,50
	100	200	2,0	1,70	1,60
	110	220	2,0	1,90	1,80
	115	230	2,0	1,95	1,85
	120	240	2,0	2,00	1,90
	125	250	2,0	2,15	2,00
	130	260	2,0	2,25	2,10
	135	270	2,0	2,35	2,20
	140	280	2,0	2,40	2,25
	150	300	2,0	2,55	2,40
	160	320	2,0	2,70	2,55
	170	340	2,0	2,85	2,70
	180	360	2,0	3,00	2,85
	190	380	2,0	3,20	3,00
	200	390	2,0	3,30	3,10
	210	400	1,9	3,45	3,25
	220	410	1,9	3,60	3,40

**Preconditioning:** ISO 187, 23°C, 50 % relative humidity

**Moisture:** 6.5 - 9 %

**Sizing:** Cobb<sub>60</sub> < 35 g/m<sup>2</sup> on request  
Cobb<sub>1800</sub> < 110 g/m<sup>2</sup> on request

Issue date 1 January 2023

[www.palm.de](http://www.palm.de)